ATAS International, Inc.
Sustainable Solutions For A Better Future

COLOR AND MATERIAL REFERENCE GUIDE

Color Description, Name	Ref. #	Steel Gauge		Aluminum Thickness								Initial Solar Reflectance	Thermal Emittance	Solar Reflectance Index (SRI)	Light Reflectance Value
Standard Colors		24	22	.032	.040	.050	.063	.080	.090	.100	.118				
Classic Bronze	1	•	•	•	•	•	•	Δ	Δ	Δ	Δ	0.12	0.82	4	4.09
Black	2	•	•	•	•	•	•	Δ	Δ	Δ	Δ	0.05	0.86	-2	5.00
Medium Bronze	3	•	•	•	•	•	•	Δ	Δ	Δ	Δ	0.33	0.86	34	11.00
Chocolate Brown	4	•	Δ	•	•	•						0.26	0.86	24	7.00
Concord Cream	5	•	Δ	•	•	•						0.65	0.85	78	62.13
Sandstone	6	•	•	•	•	•	•	Δ	Δ	Δ	Δ	0.57	0.85	66	49.76
Redwood	7	•	Δ	•	•	•						0.24	0.84	22	5.54
Mission Red	8	•	Δ	•	•	•						0.41	0.86	45	15.00
Sierra Tan	9	•	Δ	•	•	•						0.48	0.86	54	32.00
Ascot White	10	•	•	•	•	•	•	Δ	Δ	Δ	Δ	0.64	0.86	83	68.00
Forest Green	11	•	Δ	•	•	•						0.28	0.85	27	10.00
Patina Green	12	•	Δ	•	•	•						0.46	0.86	51	24.00
Dove Grey	13	•	•	•	•	•	•	Δ	Δ	Δ	Δ	0.50	0.83	55	35.18
Siam Blue	14	•	Δ	•	•	•						0.34	0.85	35	18.94
Rawhide	15	•	Δ	•	•	•						0.55	0.85	64	40.02
Rocky Grey	16	•	Δ	•	•	•						0.29	0.86	28	14.00
Regal Blue	18	•	Δ	•	•	•						0.27	0.86	26	10.00
Teal	19	•	Δ	•	•	•						0.30	0.85	30	10.56
Slate Grey	20	•	•	•	•	•	•	Δ	Δ	Δ	Δ	0.40	0.83	42	17.13
Slate Blue	21	•	Δ	•	•	•						0.31	0.86	31	18.32
Boysenberry	25	•	Δ	•	•	•						0.28	0.86	28	8.00
Bone White	26	•	•	•	•	•	•	Δ	Δ	Δ	Δ	0.74	0.86	90	76.00
Hartford Green	27	•	Δ	•	•	•						0.25	0.85	23	5.03
Hemlock Green	30	•	Δ	•	•	•						0.30	0.86	30	17.18
Charcoal Grey	62	•	•	•	•	•	•	Δ	Δ	Δ	Δ	0.29	0.82	27	10.01
55% Al-Zn Alloy Coated Steel With Acrylic Coating	97	•	Δ									0.68	0.14	58	
Mill Finish-Aluminum	99			•	•	•	•	Δ	Δ	Δ	Δ	—	—	—	

Color Description, Name	Ref. #	Steel Gauge		Aluminum Thickness								Initial Solar Reflectance	Thermal Emittance	Solar Reflectance Index (SRI)	Light Reflectance Value
Matte Finish		24	22	.032	.040	.050	.063	.080	.090	.100	.118				
Char Brown	29			•	•							.24	.84	20	4.34
Matte Black	32	•	•	•	•		Δ	Δ	Δ	Δ	Δ	.09	.84	2	3.70
Ash Grey	33	•	Δ	•	•							.50	.86	57	37.00
Thunder Grey	34	•	Δ	•	•							.26	.86	25	13.00
Almond	36	•	Δ	•	•	•						.64	.86	76	60.00
Anchor Grey	37	•	Δ	•	•							.39	.84	41	17.77

• = Stocked

Δ = 22ga steel, .080, .090, .100, & .118 aluminum are available upon request, subject to possible extended lead times.

ATAS International, Inc.
Sustainable Solutions For A Better Future

COLOR AND MATERIAL REFERENCE GUIDE

Color Description, Name		Ref. #	Steel Gauge		Aluminum Thickness								Initial Solar Reflectance	Thermal Emittance	Solar Reflectance Index (SRI)	Light Reflectance Value
Premium Finish			24	22	.032	.040	.050	.063	.080	.090	.100	.118				
Brite Red		17	•	Δ	•	•	•						0.41	0.83	43	8.22
Coppertone		23	•	Δ	•	•							0.52	0.83	58	24.54
Antique Patina		24	•	Δ	•	•							0.26	0.85	24	14.33
Silversmith		28	•	•	•	•	•	•	Δ	Δ	Δ	Δ	0.54	0.82	60	31.03
Champagne		31	•	Δ	•	•							0.59	0.82	67	38.46
Titanium		35	•	•	•	•	•	•	Δ	Δ	Δ	Δ	0.59	0.84	68	38.63

Color Description, Name		Ref. #	Steel Gauge		Aluminum Thickness								Initial Solar Reflectance	Thermal Emittance	Solar Reflectance Index (SRI)	Light Reflectance Value
Anodized			24	22	.032	.040	.050	.063	.080	.090	.100	.118				
LA Extra Dark Bronze Anodized		66				•		•					0.16	0.75	6	
BlackMatt Anodized		67				•		•								
Dark Bronze Anodized		71			•	•							0.15	0.77	6	
Clear Satin Anodized		70			•	•	•	•					0.77	0.70	92	

Color Description, Name		Ref. #	Steel Gauge		Aluminum Thickness								Initial Solar Reflectance	Thermal Emittance	Solar Reflectance Index (SRI)	Light Reflectance Value
Woodland Series			24	22	.032	.040	.050	.063	.080	.090	.100	.118				
Driftwood	–	53			•											
Cedar	–	54			•											
Walnut	–	55			•											
Birch	–	57			•											
Bamboo	–	81			•											

Color Description, Name		Ref. #	Steel Gauge		Aluminum Thickness								Initial Solar Reflectance	Thermal Emittance	Solar Reflectance Index (SRI)	Light Reflectance Value
Oxide Series			24	22	.032	.040	.050	.063	.080	.090	.100	.118				
Copper Brown	–	42				•										
Tarnished Red	–	47				•										

Color Description, Name		Ref. #	Steel Gauge		Aluminum Thickness	Initial Solar Reflectance	Thermal Emittance	Solar Reflectance Index (SRI)	Light Reflectance Value
InSpire HP			24	22	.028				
Select Blue	–	969			•				

• = Stocked

Δ = 22ga steel, .080, .090, .100, & .118 aluminum are available upon request, subject to possible extended lead times.

ATAS International, Inc. offers Sustainable Building Envelope Technology products that are coated with cool pigment paint that reflects infrared radiation, thus allowing the color to appear the same but keeping the material cooler. ATAS products may contribute to LEED ® credits and/or be rated by the CRRC ®.

The 70% PVDF finish carries a limited warranty against chalking and fading. ATAS coated materials are non-staining and virtually maintenance free. Any surface residue is easily removed with conventional cleaning solutions or detergents. Minor scratches may be touched up with an air dry touch-up coating of the same color, available from ATAS.

ATAS reserves the right to modify, eliminate and/or change its products without prior notification. Consult your ATAS representative to confirm color and material availabilities.